



**C1, Private Industrial Estate,
Pollachi Main Road,
Coimbatore-641021**

**Contact:
+91 9080759716
+91 8754928514**

Ceramic cross partition rings(4Cell):

Category	Parameter	Specification / Value
2. Chemical Composition (Ceramic)	SiO ₂	65% – 75%
	Al ₂ O ₃	20% – 30%
	Fe ₂ O ₃ + TiO ₂	1% – 3%
	K ₂ O + Na ₂ O	2% – 4%
	CaO + MgO	0.5% – 1.5%
	Water Absorption	< 1% (as per IS 7087)
3. Physical Properties	Resistance to Acid	> 99.5% by mass

4-CELL PARTITION RINGS						
Size	Dia & Height (mm)	Thickness (mm)	No. of pieces per M ³ ±10%	Wt. Per M ³ in Kgs ±10%	Surface area M ² /M ³ ±10%	% Free space
50 mm	50 ± 3	5 ± 1	5822	710	148	66
75 mm	75 ± 3	8 ± 2	1480 (Dumped)	630	96	61
			2353 (Stacked)	950	152	65
100 mm	100 ± 5	10 ± 2	1020 (Stacked)	815	99	75
150 mm	150 ± 5	15 ± 3	300 (Stacked)	960	67	60